



SG290P RESIDENTIAL LINE

MADE IN ITALY MODULE

Peimar polycrystalline solar panels made in Italy provide customers with a perfect combination of high-efficiency and versatility. Thanks to the use of highquality solar cells, our panels achieve outstanding performance and ensure maximum production output even under poor lighting and weather conditions. The strong yet ultra-light frames, available in silver or black make installation easy but robust in either residential, commercial or large-scale settings.

30 YEAR LINEAR POWER WARRANTY20 YEAR PRODUCT WARRANTY

DID

PID FREE



MODULE FIRE PERFORMANCE: CLASS 1



ABE

ANTI-REFLECTIVE GLASS

QBE INSURANCE Product Liability Insurance QBE

CELLS



60 CELLS POLY 5BB

156.75x156.75 mm / 6.17x6.17"

FRAME



COMPACT AND STURDY | 40mm

ANCHORABLE ALSO ON THE SHORT SIDE $^{\rm (5)}$



RESIDENTIAL LINE

ELECTRICAL CHARACTERISTICS (STC) (1)

290 W
0/+5 W
32.2 V
9.01 A
39.28 V
9.64 A
1500 V
15 A
17.83%
Class II

MECHANICAL CHARACTERISTICS

Solar Cells	60 (6x10) polycrystalline	
Solar Cells Size	156.75x156.75 mm / 6.17x6.17"	
Front Cover	3.2 mm / 0.13" thick, low iron tempered glass	
Back Cover	TPT (Tedlar-PET-Tedlar)	
Encapsulant	EVA (Ethylene vinyl acetate)	
Frame	Anodized aluminium alloy, double wall	
Frame finishing	Silver / Black	
Backsheet finishing	White	
Diodes	3 Bypass diodes serviceable	
Junction Box	IP67 rated	
Connector	MC4 or compatible connector	
Cables Lenght	900 mm / 35.43"	
Cables Section	4.0 mm ² / 0.006 in ²	
Dimensions	1640x992x40 mm / 64.57x39.06x1.57"	
Weight	18 Kg / 39.68 lbs	
Max Load (Test Load) - SF	5400 Pa - 1.5 (5)	


TEMPERATURE CHARACTERISTICS


NMOT (3)		45±2 °C
Temperature Coefficient of Pmax		-0.39 %/°C
Temperature Coefficient of Voc		-0.28 %/°C
Temperature Coefficient of Isc		0.042 %/°C
Operating Temperature		-40 °C ~ +85°C
PACKAGING ⁽³⁾		
Pallet dimensions	1700x1200x1200 mm / 66.93x47.24x47.24"	
Pieces per pallet	27	
Weight	516 Kg / 1138 lbs	
CERTIFICATIONS		
Fire Resistance Rating	Class of reaction to fire 1 (UNI 9177)	
PID free	IEC TS 62804-1:2015	
Salt mist	IEC 61701:2011	
Ammonia	IEC 62716:2013	

SG290P

CURRENT/VOLTAGE CHARACTERISTICS

DIMENSIONS







(1. STC: (Standard Test Condition) Irradiance 1000W/m²; Module Temperature 25°C; Air Mass 1.5

2. Pmax, Voc, Isc measurement tolerance: ±3%

3. NMOT: Nominal Module Operating Temperature: Irradiance 800W/m²; Air 20°C; Wind speed 1m/s





4. Pallets can be stacked up to two

5. Consult the installation manual for the relative mounting configurations



It is important to point out, that all technical specifications, information and figures contained in this datasheet are estimated values. Peimar reserves the right to change the technical specifications, information and figures contained in this document at any time without notice. EN_2021_12_00